



Our Know-how - Your Advantage

With soft feel and comfortable, high elasticity, UV resistant, precipitation resistant, halogen-free features, GP540 can be used for a variety of cable jacketing.

Safety first:

Standards that meet market requirements:

Halogen - free

Soft and comfortable surface


Very good sensory properties and low migration levels

Durability:

Excellent weather resistance, precipitation resistance, high elasticity Hardness ranges from Shore A 55 to Shore A 95

Typical Applications

Cable jacketing





Technical Data

Physical Property	Unit	GP540-7503(N)F	GP540-9003(N)F
Hardness	Shore	75A	90A
Density	g/cm3	1.09	1.09
Tensile Strength	MPa	4.5	6.0
Elongation at Break	%	400	250

TALK TO OUR EXPERTS!

SUNGLORY PLASTIC (VIET NAM) COMPANY LIMITED - SOUTHEAST ASIA



Candy@sungallon.com