



## Our Know-how – Your Advantage

With excellent aging resistance, high resilience, excellent compression resistance, halogen-free, fully recyclable features, GP610 can be used for safe automotive seals, door and window seals.

### Safety first:

Standards that meet market requirements:

Contains no latex, PVC, phthalates or heavy metals

Halogen-free

### Durability:

Temperature resistance

Excellent mechanical properties, such as good elasticity, aging resistance, compression deformation resistance

Hardness ranges from Shore A 40 to Shore A 90

## Typical Applications

- Automotive seals
- Door and window seals



## Technical Data

| Physical Property   | Unit  | GP610-4502 | GP610-8502 |
|---------------------|-------|------------|------------|
| Hardness            | Shore | 45A        | 70D        |
| Density             | g/cm3 | 0.96       | 0.96       |
| Tensile Strength    | MPa   | 4.0        | 9.0        |
| Elongation at Break | %     | 420        | 520        |

## TALK TO OUR EXPERTS !

SUNGLORY PLASTIC (VIET NAM) COMPANY LIMITED - SOUTHEAST ASIA



[Candy@sungallon.com](mailto:Candy@sungallon.com)